

## **Yorvik Restoration**

size 50mm & 65mm

compressive strength 25N/mm<sup>2</sup>

water absorption 17%

**durability** FL / F2

weight per pack

50mm: 1500kg, 65mm: 1600kg


pack size

50mm: 935, 65mm: 730

active soluble salts content \$2

dry weight per brick 50mm: 1.6kg, 65mm: 2.19kg

dimensional tolerences T1 Range Category R1



**call us** 01430 432667

email info@crest-bst.co.uk

www. crest-bst.co.uk

visit our showroom
Howdenshire Way
Knedlington Road
Howden
DN14 7HZ



