

Balmoral Blend

size 65mm

compressive strength 12N/mm²

water absorption 8%

durability FL / F2

weight per pack 65mm: 1200kg

pack size 65mm: 504

active soluble salts content S2

dry weight per brick 65mm: 2.35kg

(E EN 771-1 Cat. I - HD

dimensional tolerances T2 Range Category R1



call us 01430 432667

email info@crest-bst.co.uk

> www. crest-bst.co.uk

visit our showroom Howdenshire Way Knedlington Road Howden DN14 7HZ



